

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
13 March 2003 (13.03.2003)

PCT

(10) International Publication Number  
**WO 03/021033 A1**

(51) International Patent Classification<sup>7</sup>: **D21C 9/00,**  
5/00, D21H 11/20

SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN,  
YU, ZA, ZM, ZW.

(21) International Application Number: PCT/US02/13532

(22) International Filing Date: 30 April 2002 (30.04.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
09/942,468 29 August 2001 (29.08.2001) US

(71) Applicant: **KIMBERLY-CLARK WORLDWIDE, INC.** [US/US]; 401 N. Lake Street, Neenah, WI 54956 (US).

(72) Inventors: **LONSKY, Werner, Franz Wilhelm;** 34 Crestview Court, Appleton, WI 54915 (US). **NEGRI, Alberto, Ricardo;** 1127 East Capitol Drive, Appleton, WI 54911 (US).

(74) Agents: **CROFT, Gregory, E. et al.;** Kimberly-clark Worldwide, Inc., 401 N. Lake Street, Neenah, WI 54956 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Declarations under Rule 4.17:**

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations

**Published:**

- with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: ENZYMATIC TREATMENT OF PULP TO INCREASE STRENGTH

(57) Abstract: Paper making fibers are treated with certain hydrolytic enzymes, specifically including cellulases, such as truncated endo-glucanases, which have been freed of their cellulose binding domain, to generate aldehyde groups at or near the surface of the fibers. Paper sheets made from the resulting fibers exhibit improved strength characteristics relative to paper sheets made from untreated fibers.

WO 03/021033 A1

## ENZYMATIC TREATMENT OF PULP TO INCREASE STRENGTH

Background of the Invention

This application is a continuation-in-part of application serial number 09/111,511 entitled Enzymatic Treatment Of Pulp To Increase Strength and filed in the U.S. Patent and Trademark Office on July 8, 1998. The entirety of application serial number 09/111,511 is hereby incorporated by reference.

5 In the manufacture of paper products, such as facial and bath tissues and paper towels, the wet strength and the dry strength of the product are important properties. To achieve these properties, it is common practice to add certain strengthening agents to an aqueous suspension of the papermaking fibers prior to forming the paper sheet. While effective in achieving targeted strength properties, these chemicals are expensive and  
10 may be detrimental for other properties (e.g., bulk) or can cause problems for the papermaking process when the whitewater has to be reused.

Therefore, there is a need for a less expensive and more convenient method of improving the sheet strength properties of papermaking fibers.

15

Summary of the Invention

It has now been discovered that certain hydrolytic enzymes can randomly react with the cellulose chains at or near the surface of the papermaking fibers to create single aldehyde groups on the fiber surfaces which are part of the fiber. These aldehyde groups, the reducing ends left after random hydrolysis of  $\beta$ -1,4 glucosidic bonds in  
20 cellulose, become sites for cross-linking with exposed hydroxyl groups of other fibers when the fibers are formed into sheets and dried, thus increasing sheet strength. In addition, by randomly cutting or hydrolyzing the fiber cellulose chains predominantly at or near the surface of the fiber, degradation of the interior of the fiber cell wall is avoided or at least minimized. Consequently, paper or tissue made from these fibers alone, or made  
25 from blends of these fibers with untreated pulp fibers, show an increase in strength properties such as dry tensile, wet tensile, tear, z-direction tensile (surface integrity), etc.

Hence, in one aspect, the invention resides in a method for treating papermaking fibers comprising mixing an aqueous suspension of papermaking fibers and one or more hydrolytic enzymes, optionally in the presence of surfactants, optionally in the presence of

other non-cellulolytic enzymes or non-hydrolytic chemical reagents, wherein aldehyde groups are formed predominantly at or near the surface of the fibers.

In another aspect, the invention resides in a method for handling the aqueous suspension of aldehyde-rich, enzyme-treated fibers comprising mechanical beating or  
5 kneading if desired, and/or mixing with supplemental chemical additives as needed.

In yet another aspect, the invention resides in a method for making a paper sheet comprising: (a) forming an aqueous suspension of papermaking fibers treated with one or more hydrolytic enzymes capable of randomly hydrolyzing cellulose or hemicellulose to create aldehyde groups; (b) feeding the aqueous suspension into a papermaking  
10 headbox; (c) depositing the aqueous suspension onto a forming fabric, whereby the fibers are retained on the surface of the forming fabric in the form of a web while water containing the hydrolytic enzyme(s) passes through the fabric; (d) collecting and recycling the water to recombine the hydrolytic enzyme(s) with additional papermaking fibers to form an aqueous suspension; and (e) drying the web to form a paper sheet.

15 Particular hydrolytic enzymes useful for purposes of this invention are those enzymes which randomly hydrolyze cellulose and/or hemicellulose to create aldehyde groups. Such enzymes include, without limitation, cellulases, hemicellulases, *endo*-cellulases, *endo*-hemicellulases, carboxymethylcellulases ("CMCases") and *endo*-glucanases. It is known that these enzymes, in particular the cellulases, will degrade the  
20 fibrous cell wall, eventually improving pliability, flexibility or softness in coarser webs, but certainly impairing tensile properties at the same time. If these enzymes are not freed of their cellulose binding domain (a step called truncation), they require the presence of a surfactant to moderate the reaction and attain the desired hydrolysis under more controlled conditions. Particularly suitable enzymes for this purpose are truncated *endo*-  
25 glucanases and carboxymethylcellulases, which do not require the presence of a surfactant.

For the purposes of this invention, truncated monocomponent *endo*-glucanases or truncated carboxymethylcellulases can be advantageous relative to multi-component cellulases because of their purity (in particular, low or no exocellulase activity) and hence  
30 greater treatment control resulting in minimal cell wall damage. However, truncated multicomponent cellulases can also work well, since the reactivity of the *exo*-glucanase portion is severely restricted by chance. A suitable commercially available truncated *endo*-glucanase is sold by Novozymes North America, Inc. (Franklinton, North Carolina), under the name Novozyme® 613, SP 988 or Novozyme® 51016. A related CBD-free  
35 CMCase is the commercial preparation EG-40N offered by Clariant Corporation

(Charlotte, North Carolina). Still, any other hydrolytic enzymes (natural, modified or even an artificial array of peptides) which possess *endo*-glucanase or carboxymethylcellulase activity can essentially produce similar results.

Suitable papermaking fibers include any virgin or recycled papermaking fibers known in the art, particularly including softwood fibers, such as northern softwood kraft fibers, and hardwood fibers, such as eucalyptus fibers.

As mentioned above, if the hydrolytic enzyme is not truncated, the presence of a surfactant is preferred in the enzyme treatment step for optimal results. A preferred surfactant is a nonionic surfactant, commercially available Tween® 80 (ICI Specialties) or any of the other Tween® 60 series products which are POE sorbitan derivatives. Other suitable nonionioic surfactants include DI600® from High Point Chemical Corp.; DI600® is an alkoxyated fatty acid. Furthermore, aryl alkyl polyetheralcohol, e.g. Union Carbide's Triton® X-100 series of surfactants; alkyl phenyl ether of polyethylene glycol, e.g. Union Carbide's Tergitol® series of surfactants; alkylphenoethylene oxide condensation products, e.g. Rhone Poulenc, Incorporated's Igepal® series of surfactants. In some cases an anionic surfactant may be used depending on the type of pulp used. Examples of suitable anionic surfactants are: ammonium or sodium salts of a sulfated ethoxylate derived from a 12 to 14 carbon linear primary alcohol; such as Vista's Alfonic® 1412A or 1412S; and sulfonated naphthalene formaldehyde condensates, e.g. Rohm and Haas's Tamol® SN. In some cases a cationic surfactant can be used, especially when debonding is also desired. Suitable cationic surfactants include imidazole compounds, e.g. Ciba-Geigy's Amasoft® 16-7 and Sapamine® P quaternary ammonium compounds; Quaker Chemicals' Quaker® 2001; and American Cyanamid's Cyanatex®.

The amount of surfactant, if present, can be from about 0.5 to about 6 pounds per metric ton of pulp, more specifically from about 1 to about 5 pounds per metric ton of pulp, more specifically from about 2 to about 4 pounds per metric ton of pulp, and still more specifically from about 2 to about 3 pounds per metric ton of pulp. The specific amount will vary depending upon the particular enzyme being used and the enzyme dosage.

The extent of the hydrolytic modification will depend on the dosage of enzyme applied. The amount of enzyme administered can be denoted in terms of its activity (in enzymatic units) per mass of dry pulp. In general, *endo*-glucanase activity ("CMCase" activity) in cellulases can be assayed by viscosimetry using carboxymethylcellulose (CMC) as a substrate. The higher the activity in a given enzyme preparation, the more pronounced the decay of viscosity will be after a given reaction (incubation) time under predefined experimental conditions. Novo Nordisk Analytical Method 302.1/1-GB,

available on request, can be used to assay endoglucanase activity. It calls for the determination of the viscosity loss of a particular solution of CMC (such as Aqualon 7LFD, initial concentration 34gpl) after 30 minutes of incubation with a given enzyme preparation at pH 7.5 (phosphate buffer) at 40°C. The method relies on the construction of a calibration curve using a standard enzyme of known carboxymethylcellulase activity such as /S, Bagsvaerd Carezyme (batch 17-1196, nominal activity 4931 ECU/g), provided by Novozymes A, Denmark. "ECU" stands for endocellulase units. Determinations of unknown activities are done relative to the standard(s) by interpolation in the calibration curve, with all preparations reacting under the same conditions. The instrument used to measure viscosity reduction is a vibrating rod viscometer, such as the MIVI 6001 unit, manufactured by Sofraser S.A., Villemandeur, France. Still, any other type of viscometer could be used, provided that the same CMC grade is used, a known CMCase standard is employed and the same incubation conditions are followed.

For purposes of this invention, enzyme dosages can vary depending on the desired extent of the treatment and can be from about 5000 to about 200,000 ECU/kilogram of oven dry fibers, more specifically from about 10,000 to about 100,000 ECU/kg, more specifically from about 10,000/kg to about 75,000 ECU/kg, and still more specifically from about 12,000 to about 60,000 ECU/kg. Mixing is desirable to achieve initial homogeneous dispersion and continuous contact between the enzyme and the substrate.

The consistency of the aqueous fiber suspension (weight percent fiber in the total pulp slurry) can be accommodated to meet usual paper mill practices. Low consistencies of about 1% or lower are workable; and consistencies as high as 16% still show sufficient enzyme activity in a pulper. For economical reasons, a consistency in the range of about 8 to about 10% is advantageous.

The reaction conditions for these enzymes can be chosen to provide a pH of about 4 to about 9, more specifically from about 6 to about 8. Temperatures can range from about 0°C (above freezing) to about 70°C. However, it can be envisioned that in the future thermostabilized *endo*-glucanases could react more effectively at extreme temperatures (such as at the boiling point of water), or that alkali-stabilized *endo*-glucanases could react efficiently at high pH ranges (for instance at pH above 11).

Reaction times are also very flexible and depend on the application of enzyme and on the desired extent of the modification. But if kept short, fiber cell wall damage is avoided even with regular cellulases especially in the presence of surfactants. In general,

suitable reaction times can be from about 10 to about 180 minutes, more specifically from about 15 to about 60 minutes.

A measure of the effectiveness of the enzyme treatment is the increase in the "copper number" of cellulose. The copper number is defined as the number of grams of copper resulting from the reduction of cupric sulfate by 100 grams of pulp. The procedure for determining the copper number is described in TAPPI Standard T 430 om-94 "Copper Number of Pulp". Historically, copper number determinations have been used to detect damage to cellulose after hydrolytic or specific oxidative treatments. An increase in reducing groups can indicate deterioration that will have a detrimental impact on mechanical strengths, since the evolution of aldehyde groups has been normally proportional to the random split of the cellulose chain and the decrease of its degree of polymerization throughout the fiber. However, for purposes of this invention, the copper number measures the improvement in the cross-linking ability of the fibers since the chemical modification is substantially restricted to the surface or the surface-near region of the fibers so as to maintain the integrity of the fiber cell walls. In general, the fibers treated in accordance with this invention have a copper number of about 0.10 or more grams of copper per 100 grams of oven-dried pulp, more specifically from about 0.10 to about 1.0 gram of copper per 100 grams of oven-dried pulp, and still more specifically from about 0.15 to about 0.70 gram of copper per 100 grams of oven-dried pulp.

The strength increases associated with the treated fibers of this invention, as measured by the dry tensile strength of handsheets made from the treated fibers of this invention compared to the dry tensile strength of handsheets made with untreated fibers, is about 40 percent or greater, more specifically about 50 percent or greater, more specifically about 60 percent or greater, more specifically about 70 percent or greater, more specifically from about 40 to about 150 percent, more specifically from about 50 to about 140 percent, still more specifically from about 60 to about 140 percent, and still more specifically from about 80 to about 140 percent. These strength increases are attributable solely to the enzymatic treatment of the fibers and is without the assistance or contribution of any other supplemental additive(s) or mechanical action that alters the fiber structure, such as refining.

Dried paper made from the treated fibers of this invention can be repulped, a new handsheet formed and dried without significant loss of the dry tensile strength.

### Examples

#### Example 1.

In order to illustrate the method of this invention, two different common  
5 papermaking fiber pulps were treated with a truncated *endo*-glucanase in accordance with  
this invention. More specifically, northern softwood bleached kraft fibers, and in a  
separate experiment, Brazilian eucalyptus bleached kraft pulp fibers, were treated with  
83,000 ECU/Kg of Novozyme 613® for 15 to 60 minutes in a hydropulper at 8%  
consistency, 40°C and a pH of 7. The reaction was terminated with the addition of sodium  
10 hypochlorite to deactivate the enzyme. After treatment, the increase of fiber surface  
aldehyde groups was measured using the copper number determination.

Table 1 shows the increase of the copper numbers for the two fully bleached kraft  
pulps before and after treatment of the fibers with Novozyme 613®. The data listed in  
Table 1 under Reaction Time 0 is an indication for the number of aldehyde groups  
15 originally present throughout the fibers and not only for those placed on the fiber surfaces.  
To avoid the loss in mechanical strength through hydrolysis, it is essential to restrict the  
extent of chemical modification to the surface of the fibers, so as to maintain the integrity  
of the cell wall.

Table 1

Copper Number Determination After Hydrolysis with Novozyme 613®

Reaction Time (min)	Northern Softwood	Eucalyptus
0	0.06	0.07
30	0.17	0.29
60	0.18	0.32

As shown by the data, both fiber types underwent an increase in copper number,  
25 indicating an increase in the number of aldehyde groups created by the action of the  
enzyme at the surface or surface-near regions of the fiber.

Example 2.

In order to illustrate the improvement in strength properties imparted to paper sheets made with the fibers treated in accordance with this invention, handsheets were made from northern softwood bleached kraft pulp and eucalyptus bleached kraft pulp fibers treated with the enzyme as described above (dosage 83,000 ECU/kg of oven-dried fibers). More specifically, handsheets having a basis weight of 60 grams per square meter were prepared by diluting a fiber sample in water to a consistency of 1.2 weight percent in a British Pulp Disintegrator and allowing the dispersed sample to soak for 5 minutes. The sample was then pulped for 5 minutes at ambient temperature, diluted to 0.3 percent consistency and formed into a handsheet on a square (9x9 inches) Valley Handsheet Mold (Voith Inc., Appleton, WI). The handsheet is couched off the mold by hand using a blotter and pressed wire-side up at 100 pounds per square inch for 1 minute. Then the handsheet was dried wire-side up for 2 minutes to absolute dryness using a Valley Steam Hotplate (Voith Inc., Appleton, WI) and a standard weighted canvas cover having a lead-filled (4.75 pounds) brass tube at one end to maintain uniform tension. The resulting handsheet was then conditioned in a humidity-controlled room (23°C, 50% relative humidity) prior to testing.

For comparison, the same northern softwood bleached Kraft fibers were treated with 83,000 ECU/Kg of Novozyme 476® –a “full” monocomponent endoglucanase, a CMCase that contains its cellulose binding domain– under identical experimental conditions.

Testing of the handsheet strength properties involved three different measures: dry tensile strength, wet tensile strength, and tear index.

Dry tensile strength is the peak load measured at the point of failure of a handsheet strip 1 inch wide and 5 inches long in an Instron Testing Machine Mini 55, running at a loading rate of 0.5 inch per minute.

Wet tensile strength is the peak load measured at the point of failure of a handsheet strip 1 inch wide and 5 inches long in an Instron Testing Machine Mini 55, running at a loading rate of 0.5 inch per minute, where the handsheet strip is wetted thoroughly as described in Tappi Standard T456 om-87.

Tear index is measured as described in Tappi Standard T220 sp-96.

Tables 2 and 3 below summarize the results.



Table 2

Northern Softwood Bleached Kraft Pulp Treated with CBD-Free  
Endoglucanase

5

Reaction Time	Incremental Dry Tensile Strength Change	Incremental Wet Tensile Strength Change	Incremental Tear Index Change
(min)	%	%	%
0	0	0	0
15	17	-1	44
30	58	33	50
60	66	28	29

Table 3

Eucalyptus Bleached Kraft Pulp Treated with CBD-Free Endoglucanase

10

Reaction Time	Incremental Dry Tensile Strength Change	Incremental Wet Tensile Strength Change	Incremental Tear Index Change
(min)	%	%	%
0	0	0	0
15	32	29	-7
30	37	48	46
60	39	20	70

The results show an increase in both dry and wet tensile strengths of the handsheets (either softwood or hardwood fibers) with time of treatment. Tear strength also increased, in contrast with the marked reduction when a full endoglucanase (containing its cellulose binding domain) is used for treatment under the same conditions (see Table 4). Table 4 summarizes the results of treatment of northern softwood Kraft fibers with Novozyme® 476. In this case, tear strength drops dramatically, showing that

the intrinsic strength of the fibers has been debilitated. These results are a clear demonstration of the ability of CBD-free endoglucanases to restrict the hydrolytic effect to the outer layers of the fiber, without damage to the bulk phase.

5

Table 4Northern Softwood Bleached Kraft Pulp Treated with Full Endoglucanase

Reaction Time	Incremental Tear Index Change
(min)	%
0	0
15	-69
30	-78
60	-83

10

Example 3.

In order to further illustrate the improvement in strength properties imparted to paper sheets made with the fibers treated in accordance with this invention, handsheets were made from northern softwood bleached kraft pulp treated with CBD-free endoglucanase Novozyme 988® under experimental conditions as described above (dosage 14,000 ECU/kg of oven-dried fibers). Table 5 below summarizes the results.

Table 5  
Northern Softwood Bleached Kraft Pulp Treated with Novozyme 988®

Reaction Time  (min)	Incremental Dry Tensile Strength Change %
0	0.0
30	79
60	111
120	136

5

Example 4.

At the end of the fiber treatment reaction, enzymatic activity can be slowed down by removal of excess liquor (thickening and dilution) which contains the enzyme. Table 6 below shows the activity of an original solution and that of a recovered filtrate and a

10 washing liquor.

More specifically, a northern softwood kraft pulp sample (30 g.o.d.) was treated at 5% consistency with a dose of Novozyme® 613 equivalent to 83,000 ECU/kg. After one hour of gentle mixing at 45°C at pH 7, the pulp slurry was filtered under vacuum to form a fiber mat of approx. 15% consistency. The corresponding filtrate of 400mL had an  
 15 enzyme activity of 2.42 ECU/mL (1). This represents a total activity of 968 ECU or 39% recovery of the initial enzyme activity.

In a continuation of the previous experiment, the filtered pulp was further washed repeatedly by diluting the filtered fiber mat to 5% consistency and re-thickening it to approx. 15%. The produced washings (taken to a total final volume of 3.5Lts.) still  
 20 showed an enzyme activity of 0.33 ECU/mL (2), corresponding to a cumulative enzyme recovery of 85% of the theoretical amount when added to the activity in the first filtrate (1+2).

The recovered excess liquor can be recycled back into the enzymatic treatment process leading to significant cost reductions through the partial reuse of the enzyme-  
 25 containing filtrate. If, however, complete inactivation of the enzyme is needed, different physical (e.g., heat) or chemical (e.g., oxidants such as hypochlorite) quenching alternatives are possible to induce irreversible denaturation of any residual enzyme.

Table 6Enzymatic Activity Novozyme® 613 Solutions Recovered by Filtration

Sample	Filtrate ECU/mL	Activity ECU	Recovery %
initial	4.35	2490	-
<u>1</u>	2.42	968	39
<u>2</u>	0.33	1155	46
<u>1 + 2</u>		2123	85

- 5 The results of Table 6 show that most of the enzyme activity can be recovered using ordinary dewatering.

It will be appreciated that the foregoing examples, given for purposes of illustration, are not to be construed as limiting the scope of the invention, which is defined by the following claims and all equivalents thereto.

We claim:

1. A method of treating papermaking fibers comprising mixing an aqueous suspension of papermaking fibers and one or more hydrolytic enzymes capable of randomly hydrolyzing cellulose and/or hemicellulose in an amount of from about 5000 to about 200,000 ECU per kilogram of fiber, wherein the dry tensile strength of handsheets made with the treated fibers, as compared to the dry tensile strength of handsheets made with untreated fibers, is increased about 40 percent or greater without the assistance of any other supplemental additive(s) or mechanical action.
2. The method of claim 1 wherein the dry tensile strength is increased about 50 percent or greater.
3. The method of claim 1 wherein the dry tensile strength is increased about 60 percent or greater.
4. The method of claim 1 wherein the dry tensile strength is increased about 70 percent or greater.
5. The method of claim 1 wherein the dry tensile strength is increased from about 40 to about 150 percent.
6. The method of claim 1 wherein the dry tensile strength is increased from about 50 to about 140 percent.
7. The method of claim 1 wherein the dry tensile strength is increased from about 60 to about 140 percent.
8. The method of claim 1 wherein the dry tensile strength is increased from about 80 to about 140 percent.
9. The method of claim 1 wherein the aqueous suspension of papermaking fibers includes a surfactant.

10. The method of claim 1 wherein the hydrolytic enzyme is selected from the group consisting of cellulases, hemicellulases, *endo*-cellulases, *endo*-hemicellulases, carboxymethylcellulases and *endo*-glucanases.
11. The method of claim 1 wherein the hydrolytic enzyme is selected from the group consisting of truncated cellulases, truncated hemicellulases, truncated *endo*-cellulases, truncated *endo*-hemicellulases, truncated carboxymethylcellulases and truncated *endo*-glucanases.
12. The method of claim 1 wherein the hydrolytic enzyme is a truncated *endo*-glucanase or truncated carboxymethylcellulase.
13. The method of claim 1 wherein the aqueous suspension has a consistency of from about 1 to about 16 percent.
14. The method of claim 1 wherein the aqueous suspension has a consistency of from about 8 to about 10 percent.
15. The method of claim 1 wherein the temperature of the aqueous suspension is from about 0°C to about 100°C.
16. The method of claim 1 wherein the temperature of the aqueous suspension is from about 20°C to about 70°C.
17. The method of claim 1 wherein the pH of the aqueous suspension is from about 4 to about 9.
18. The method of claim 1 wherein the pH of the aqueous suspension is from about 6 to about 8.
19. The method of claim 1 wherein the dosage of the hydrolytic enzyme is from about 10,000 to about 100,000 ECU per kilogram of oven-dried pulp.

20. The method of claim 1 wherein the dosage of the hydrolytic enzyme is from about 10,000 to about 75,000 ECU per kilogram of oven-dried pulp.
21. The method of claim 1 wherein the aqueous suspension of papermaking fibers and the hydrolytic enzyme is mixed for a time of from about 10 to about 180 minutes.
22. The method of claim 1 wherein the aqueous suspension of papermaking fibers and the hydrolytic enzyme is mixed for a time of from about 15 to about 60 minutes.
23. The method of claim 1 wherein the resulting treated fibers have a copper number of about 0.10 or more grams of copper per 100 grams of oven-dried pulp.
24. The method of claim 1 wherein the resulting treated fibers have a copper number of from about 0.10 to about 1 gram of copper per 100 grams of oven-dried pulp.
25. The method of claim 1 wherein the resulting treated fibers have a copper number of from about 0.15 to about 0.50 gram of copper per 100 grams of oven-dried pulp.
26. A method of making a paper sheet comprising:
  - (a) forming an aqueous suspension of papermaking fibers pretreated with a dosage of a hydrolytic enzyme capable of randomly hydrolyzing cellulose and/or hemicellulose, said dosage being from about 5000 to about 200,000 ECU per kilogram of oven dry fiber, wherein aldehyde groups are formed predominantly on the surface of the fibers;
  - (b) feeding the aqueous suspension into a papermaking headbox;
  - (c) depositing the aqueous suspension onto a forming fabric, whereby the fibers are retained on the surface of the forming fabric in the form of a web while water containing the hydrolytic enzyme passes through the fabric;
  - (d) collecting and recycling the water to recombine the hydrolytic enzyme with additional papermaking fibers to form an aqueous suspension; and
  - (e) drying the web to form a paper sheet.

27. The method of claim 26 wherein the dosage is from about 10,000 to about 100,000 ECU/kilogram of oven dry fiber.
28. The method of claim 26 wherein the dosage is from about 10,000 to about 75,000 ECU/kilogram of oven dry fiber.
29. The method of claim 26 wherein the dosage is from about 12,000 to about 60,000 ECU/kilogram of oven dry fiber.
30. The method of claim 26 wherein the aqueous suspension of papermaking fibers includes a surfactant.
31. The method of claim 26 wherein the hydrolytic enzyme is selected from the group consisting of cellulases, hemicellulases, *endo*-cellulases, *endo*-hemicellulases and *endo*-glucanases.
32. The method of claim 26 wherein the hydrolytic enzyme is selected from the group consisting of truncated cellulases, truncated hemicellulases, truncated *endo*-cellulases, truncated *endo*-hemicellulases and truncated *endo*-glucanases.
33. The method of claim 26 wherein the hydrolytic enzyme is a truncated *endo*-glucanase.
34. The method of claim 26 wherein the aqueous suspension has a consistency of from about 1 to about 16 percent.
35. The method of claim 26 wherein the aqueous suspension has a consistency of from about 8 to about 10 percent.
36. The method of claim 26 wherein the temperature of the aqueous suspension of papermaking fibers and hydrolytic enzyme is from about 0°C to about 100°C.
37. The method of claim 26 wherein the temperature of the aqueous suspension of papermaking fibers and hydrolytic enzyme is from about 20°C to about 70°C.



38. The method of claim 26 wherein the pH of the aqueous suspension of papermaking fibers and hydrolytic enzyme is from about 4 to about 9.
39. The method of claim 26 wherein the pH of the aqueous suspension of papermaking fibers and hydrolytic enzyme is from about 6 to about 8.
40. The method of claim 26 wherein the aqueous suspension of papermaking fibers and the hydrolytic enzyme is mixed for a time of from about 10 to about 180 minutes.
41. The method of claim 26 wherein the aqueous suspension of papermaking fibers and the hydrolytic enzyme is mixed for a time of from about 15 to about 60 minutes.
42. The method of claim 26 wherein the treated fibers from step (a) have a copper number of about 0.10 or more grams of copper per 100 grams of oven-dried pulp.
43. The method of claim 26 wherein the treated fibers from step (a) have a copper number of from about 0.10 to about 1 gram of copper per 100 grams of oven-dried pulp.
44. The method of claim 26 wherein the treated fibers from step (a) have a copper number of from about 0.15 to about 0.50 gram of copper per 100 grams of oven-dried pulp.

International Application No  
PCT/US 02/13532

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> IPC 7    D21C9/00    D21C5/00    D21H11/20		
According to International Patent Classification (IPC) or to both national classification and IPC		
<b>B. FIELDS SEARCHED</b> Minimum documentation searched (classification system followed by classification symbols) IPC 7    D21C    D21H		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) PAJ, EPO-Internal, WPI Data		
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 045 500 A (HITACHI LTD) 10 February 1982 (1982-02-10) abstract page 2, paragraph 2 table 1	1, 26
Y	WO 91 17243 A (NOVONORDISK AS) 14 November 1991 (1991-11-14) example 8	1, 26
Y	US 6 241 849 B1 (FRANKS NEAL E) 5 June 2001 (2001-06-05) claims 1, 18-20 example 1	1, 26
--- -/---		
<div style="display: flex; justify-content: space-between;"> <div> <input checked="" type="checkbox"/> Further documents are listed in the continuation of box C.         </div> <div> <input checked="" type="checkbox"/> Patent family members are listed in annex.         </div> </div>		
<b>* Special categories of cited documents :</b>		
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p>*A* document defining the general state of the art which is not considered to be of particular relevance</p> <p>*E* earlier document but published on or after the international filing date</p> <p>*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>*O* document referring to an oral disclosure, use, exhibition or other means</p> <p>*P* document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>*Z* document member of the same patent family</p> </div> </div>		
Date of the actual completion of the international search	Date of mailing of the international search report	
16 July 2002	29/07/2002	
Name and mailing address of the ISA	Authorized officer	
European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Naeslund, P	

# INTERNATIONAL SEARCH REPORT

International Application No  
PC1/JS 02/13532

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5 990 283 A (MCQUEEN-MASON SIMON ET AL) 23 November 1999 (1999-11-23) column 23, line 16 -column 24, line 22; example 18 ---	1,26
Y	DATABASE WPI Section Ch, Week 199648 Derwent Publications Ltd., London, GB; Class D16, AN 1996-482787 XP002206253 & JP 08 246368 A (MITSUBISHI PAPER MILLS LTD), 24 September 1996 (1996-09-24) abstract ---	1,26
A	US 6 117 664 A (HANSEN SVEND AAGE ET AL) 12 September 2000 (2000-09-12) ---	
A	DATABASE WPI Section Ch, Week 199824 Derwent Publications Ltd., London, GB; Class A11, AN 1998-271795 XP002206254 & WO 98 17854 A (KAO CORP), 30 April 1998 (1998-04-30) abstract -----	

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PC, JS 02/13532

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0045500	A	10-02-1982	JP 1230792 C	26-09-1984
			JP 57029293 A	17-02-1982
			JP 59007439 B	18-02-1984
			BR 8104871 A	13-04-1982
			DE 3172721 D1	28-11-1985
			EP 0045500 A1	10-02-1982
			US 4451567 A	29-05-1984
WO 9117243	A	14-11-1991	AT 118545 T	15-03-1995
			AU 639570 B2	29-07-1993
			AU 7887491 A	27-11-1991
			BR 9106435 A	04-05-1993
			CA 2082279 A1	10-11-1991
			DE 69107455 D1	23-03-1995
			DE 69107455 T2	12-10-1995
			WO 9117243 A1	14-11-1991
			DK 531372 T3	10-07-1995
			EP 0531372 A1	17-03-1993
			ES 2068586 T3	16-04-1995
			FI 925079 A	09-11-1992
			JP 2000217583 A	08-08-2000
			JP 3110452 B2	20-11-2000
			JP 5509223 T	22-12-1993
			JP 2001057894 A	06-03-2001
			KR 237148 B1	15-01-2000
			US 5948672 A	07-09-1999
			US 2001036910 A1	01-11-2001
US 6241849	B1	05-06-2001	US 2001047852 A1	06-12-2001
			AU 6046199 A	03-04-2000
			BR 9913793 A	16-10-2001
			EP 1129252 A1	05-09-2001
			WO 0015899 A1	23-03-2000
US 5990283	A	23-11-1999	US 6326470 B1	04-12-2001
			US 6255466 B1	03-07-2001
			US 5959082 A	28-09-1999
JP 8246368	A	24-09-1996	NONE	
US 6117664	A	12-09-2000	AU 1890095 A	25-09-1995
			WO 9524471 A1	14-09-1995
			EP 0749473 A1	27-12-1996
			US 5912157 A	15-06-1999
WO 9817854	A	30-04-1998	WO 9817854 A1	30-04-1998
			JP 10183478 A	14-07-1998